



Article Number: 308-30921

Heat Shrink Tubing, HIS-3-Bag, 3:1 Shrink Ratio, 3/8", 9.5/3.0 Dia, PO, Clear, 10/pkg Description:

Base Data		
	Local Order Number	308-30921
	Type	HIS-3-BAG 9/3 CL
	•	
	Color	Clear (CL)
	Features and Benefits	 Thin wall, flexible 3 to 1 shrink ratio material accommodates a wide range of component shapes and diameters. Meets UL224 VW-1 specifications, making it ideal for high heat applications (excludes clear tubing). Polyolefin material provides excellent insulation and mechanical strength with good resistance to solvents, oils and fuels. Available in bulk reels, sticks and convenience bags (HIS-3 bags), for small to large volume applications.
	Quantity Per	bag
	Product Description	TFN31 series heat shrink tubing features a flexible, thin wall and highly flame retardant polyolefin material with a higher operating temperature range than general-use heat shrink tubing. and offers good resistance to solvents, oils and fuels. The 3 to 1 shrink ratio accommodates a variety of component shapes and sizes. TFN31 tubing is available in bulk reels, sticks and convenience bags (HIS-3 bags), for projects of all sizes.
	Short Description	Heat Shrink Tubing, HIS-3-Bag, 3:1 Shrink Ratio, 3/8", 9.5/3.0 Dia, PO, Clear, 10/pkg
Product Dimensions		
	Length L (Metric)	200mm
	Length L3 (imperial)	6.0"
	Length L3 (metric)	152.4mm
	Printable (Yes/No)	No
	Shrink Ratio	3:1
	Trade Size	3/8 "
	Variant	Thin-Wall
	Volume Resistance (Ohm cm)	10 ¹⁴ Ω cm (ASTM D 876)
	Nominal Diameter (Imperial)	3/8"
	Nominal Diameter (Metric)	9.5mm
	Wall Thickness WT (Imperial)	.029"

generated on:

4/28/2017

308-30921



Product Dimensions Wall Thickness WT (Metric) Recovered Diameter d (metric) Recovered Diameter d (imperial) Supplied Diameter D (imperial) Supplied Diameter D (metric)	.75mm 3.0mm 0.118" 0.38" 9.5mm
Recovered Diameter d (metric) Recovered Diameter d (imperial) Supplied Diameter D (imperial)	0.118"
Supplied Diameter D (imperial)	0.38"
Supplied Diameter D (metric)	9.5mm
Material and Specifications	
Material	Polyolefin, cross-linked (PO-X)
Material Shortcut	PO-X
Dielectric Strength (Metric)	20 kV/mm according to ASTM D 150
Elongation at break	800% nach ASTM D2671
Flammability	UL224 VW-1 (except clear)
Shrink Temperature	+212 °F (+100 °C)
Operating Temperature	-67°F to +275°F (-55°C to +135°C)
ROHS Compliant	Yes
Certification/Specification	UL ANSI/UL 224
Logistic and Packaging	
Package Quantity (Imperial)	10
Package Quantity (Metric)	10Pieces
Customs Number(Schedule B)	3926909987

generated on: 4/28/2017